


BLACK TUXEDO WS FSC™ / AP1300 / WG74

PRODUCT  
DESCRIPTION /  
BENEFITS

**Face :** Natural smooth black paper wet strength. FSC certified.

**Adhesive :** Acrylic permanent adhesive featuring good clarity and water resistance.

**Liner :** White supercalendered glassine paper. There may be slight variations in tone.



FEATURES

ICE BUCKET



WET OPACITY



FRIDGE



TYPICAL USE

Wine, Spirits & Craft Beer

PRODUCT  
RECOMMENDATIONS

Ideal for high quality labels for beverages, wine and promotional uses. Excellent water resistance with good stability after immersion in ice and water.

Not suggested for neck labels and small diameter bottles.

The performance of the material on non perfectly cylindrical containers must be validated for the specific product application.

REELS MUST BE WOUND WITH THE FACE-SIDE OUT.

Ideal for high quality labels for beverages, wine and promotional uses. Excellent water resistance with good stability after immersion in ice and water.

Not suggested for neck labels and small diameter bottles.

The performance of the material on non perfectly cylindrical containers must be validated for the specific product application.

REELS MUST BE WOUND WITH THE FACE-SIDE OUT.

SHELF LIFE

2 years, under storage conditions as defined by FINAT section 2.5 (20-25°C, 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life of the product.

## BLACK TUXEDO WS FSC™ / AP1300 / WG74

### PHYSICAL PROPERTIES / TYPICAL VALUES

#### FACE MATERIAL

##### BLACK TUXEDO WS FSC™

Grammage	90 Gr/m2	ISO 536
Thickness	113 µm	ISO 534-80

#### ADHESIVE

##### AP1300

Tack (N) Glass	9 N/mm	FTM9
Min Labelling temperature	+5 °C	
Usage Temperature	-40/+80°C °C	

#### LINER

##### WG74

Grammage	72 Gr/m2	ISO 536
Thickness	62 µm	ISO 534-80

### QUALITY CERTIFICATIONS & APPROVALS

- FSC License code: FSC-C106281

### DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.